

SECTION 1300N

FOOTAGE	DESCRIPTION	SAMPLE NUMBER	SAMPLE LENGTH	GOLD ASSAYS	
				OZ./TON	OZ./TON
0 - 20.5	Gry ser sch, few qtz lenses, no sig min.				
20.5 - 24.0	30% qtz-carb in ser sch, py.	3970	3.5	.02	
24.0 - 49.5	Gry ser sch, py. T. S. Min qtz 34.0-36.0	3971	2.0	.02	
49.5 - 54.5	Sect. ore type in gry ser sch, py, aspy.	3978	5.0	.59	
54.5 - 81.5	Gry ser sch local qtz & min. T. S. 68.5 - 70.5 T. S. 78.0 - 79.0	3979	2.0	.05	
		3980	1.0	.01	
81.5 - 88.0	50% qtz w ep & local gry min, py, aspy.	3981	6.5	.99	6.435
88.0 - 96.0	As above, sharp fault contact w $\frac{1}{2}$ " gauge 96.0	3982	8.0	.39	3.120
					9.555
96.0 - 121.0	F.g. grs sch.				
121.0 - 141.0	F. g. sch grs, chty - ep sect.				
		Calc. Grade.			
		From	To	C.L.	Uncut Cut.
		49.5	54.5	5.0	.59 ---
		81.5	96.0	14.5	.66 .66

Hole No. U-B 478