

GIANT YELLOWKNIFE GOLD MINES LIMITED
CORE RECORD

HOLE No. U-B 622SHAFT 2BEARING --LEVEL 575DIP AT COLLAR -90°LAT. 13,029.0DATE COMPLETED October 12, 1949DEP. 7,698.5PURPOSE Deep Ore ExplorationWORKING B405E X-CLENGTH 361.0ELEV. 5,434.5SECTION 1300N

FOOTAGE	DESCRIPTION	SAMPLE NUMBER	SAMPLE LENGTH	GOLD ASSAYS	
				OZ./TON	OZ./TON
0.0 - 2.0	casing				
2.0 - 20.0	Fg gray-grn chl-ser sch				
20.0 - 46.0	Fg gray ser sch				
46.0 - 62.0	Fg gray-grn ser sch with local carb lenses				
62.0 - 103.0	Fg light gray ser sch with local qutzz-carb lenses and neg min				
103.0 - 123.5	M to fg gray ser sch				
123.5 - 128.0	80% qutzz-carb spar min with py aspy and traces of sph	6681	4.5	.38	1.710
128.0 - 135.0	20% qutzz-carb lenses in ser sch spar min with py and aspy	6682	7.0	.13	.910
135.0 - 140.0	70% qutzz with minor carb spar min with py aspy and sph	6683	5.0	.93	4.650
140.0 - 145.0	as above	6684	5.0	.77	3.850
145.0 - 150.0	40% qutzz-carb lenses and as above	6685	.29	5.0	1.450
150.0 - 156.0	as above	6686	.44	6.0	2.640
156.0 - 162.0	as above	6687	.08	6.0	.480
162.0 - 167.0	60% qutzz with minor carb min with py and aspy	6688	5.0	.55	2.750

Logged by J.A.H.Hole No. U-B 622

FOOTAGE	DESCRIPTION	SAMPLE NO.	SAMPLE LENGTH	GOLD ASSAYS	
				oz./TON	oz./TON
167.0 - 172.0	40% qutzz-carb lenses and as above	6689	5.0	.54	2.700
172.0 - 178.0	as above	6690	6.0	.34	2.040
178.0 - 185.5	Fg gray ser sch				<u>23.230</u>
185.5 - 187.0	40% bx qutzz well min with aspy and minor py	6691	1.5	.56	
187.0 - 197.0	Fg gray ser sch				
197.0 - 202.0	50% qutzz in ser sch min with py and aspy	6692	5.0	.31	1.550
202.0 - 208.0	as above but with increasing carb	6693	6.0	.11	.660
208.0 - 232.0	Fg dark gray ser sch with local qutzz-carb lenses				<u>2.210</u>
232.0 - 254.0	Fg light gray ser sch with numerous qutzz-carb lenses				
254.0 - 296.5	Very fg light gray chert-like ser sch 4' ground at 285.0				
296.5 - 303.0	50% by qutzz-carb min with py and aspy	6694	6.5	.78	5.070
303.0 - 314.0	Fg gray-grn ser sch				
314.0 - 319.0	30% qutzz-carb lenses in ser sch min with py and aspy	6695	5.0	.12	
319.0 - 325.0	Fg light gray ser sch with local qutzz-carb lenses spar min	6696	6.0	.04	
325.0 - 330.0	40% qutzz in ser sch very well min with fine aspy, in part mass aspy for short sections, minor py, sph and gray min	6697	5.0	.46 .48	2.350
330.0 - 334.5	60% qutzz in ser sch very well min with aspy and minor py, short sections of mass aspy as above	6718	4.5	.91 1.07	4.455
334.5 - 339.5	90% blue qutzz, minor carb well min with py, aspy, sph and gray min, possible V.G. at 339.0	6719	5.0	.39 .46	2.100
339.5 - 345.0	40% qutzz-carb lenses in ser sch min with py, aspy, gray min and sph	6720	5.5	.17 .21	<u>1.045</u>
					9.950

FOOTAGE	DESCRIPTION	SAMPLE No.	SAMPLE LENGTH	GOLD ASSAYS																															
				OZ./TON	OZ./TON																														
345.0 - 349.5	20% qutz-carb lenses in ser sch spar min with py and aspy	6721	4.5	.07																															
349.5 - 353.0	as above	6722	3.5	.04																															
353.0 - 361.0	Fg light gray ser sch																																		
	<table><tr><td></td><td><u>From</u></td><td><u>To</u></td><td><u>C.L.</u></td><td><u>Calc. Grade</u></td></tr><tr><td></td><td>123.5</td><td>178.0</td><td>54.5</td><td>.42</td></tr><tr><td></td><td>185.5</td><td>187.0</td><td>1.5</td><td>.56</td></tr><tr><td></td><td>197.0</td><td>208.0</td><td>11.0</td><td>.22</td></tr><tr><td></td><td>296.5</td><td>303.0</td><td>6.5</td><td>.78</td></tr><tr><td></td><td>325.0</td><td>345.0</td><td>20.0</td><td>.50</td></tr></table>		<u>From</u>	<u>To</u>	<u>C.L.</u>	<u>Calc. Grade</u>		123.5	178.0	54.5	.42		185.5	187.0	1.5	.56		197.0	208.0	11.0	.22		296.5	303.0	6.5	.78		325.0	345.0	20.0	.50				
	<u>From</u>	<u>To</u>	<u>C.L.</u>	<u>Calc. Grade</u>																															
	123.5	178.0	54.5	.42																															
	185.5	187.0	1.5	.56																															
	197.0	208.0	11.0	.22																															
	296.5	303.0	6.5	.78																															
	325.0	345.0	20.0	.50																															
	<table><tr><td colspan="3"><u>Dip tests</u></td></tr><tr><td><u>At.</u></td><td><u>Angle Read.</u></td><td><u>Corrected Angle</u></td></tr><tr><td>150'</td><td>80°</td><td>77°</td></tr><tr><td>300'</td><td>72°</td><td>68½°</td></tr></table>	<u>Dip tests</u>			<u>At.</u>	<u>Angle Read.</u>	<u>Corrected Angle</u>	150'	80°	77°	300'	72°	68½°																						
<u>Dip tests</u>																																			
<u>At.</u>	<u>Angle Read.</u>	<u>Corrected Angle</u>																																	
150'	80°	77°																																	
300'	72°	68½°																																	