

SECTION 750N

FOOTAGE	DESCRIPTION	SAMPLE NUMBER	SAMPLE LENGTH	GOLD ASSAYS	
				OZ./TON	OZ./TON
0 - 13.0	F.g. grn grs sch				
13.0 - 22.0	grn chl-ser sch				
22.0 - 28.0	qtz-carb lenses in ser sch; minor min	7735	6.0	.04	
28.0 - 32.0	As above	7736	4.0	.58	2.320
32.0 - 37.0	50% qtz-carb; large xls aspy; local gry min	7737	5.0	.16	.800
37.0 - 42.0	As above	7738	5.0	.12	.600
42.0 - 49.0	As above	7739	7.0	.31	2.170
49.0 - 54.0	As above	7740	5.0	.22	1.100
54.0 - 61.0	As above	7742	7.0	.44	3.080
61.0 - 68.0	As above	7743	7.0	.20	1.400
68.0 - 75.0	As above	7744	7.0	.13	<u>.910</u>
75.0 - 83.0	buff ser sch w lge idiom xls aspy				12.380
	From To C.L.				
	28.0 75.0 47.0				
					<u>Grade</u>
					.26

Hole No. U-3773