

# GIANT YELLOWKNIFE GOLD MINES LIMITED

## CORE RECORD

HOLE No. U-B 192BEARING N 60 WDIP AT COLLAR HorLENGTH 130LAT. 12 164DEP. 7199ELEV. 5902DATE COMPLETED April 6, 1947PURPOSE Ore definitionSHAFT 2LEVEL 100WORKING 106 N drSECTION 300 N

FOOTAGE	DESCRIPTION	SAMPLE NUMBER	SAMPLE LENGTH	GOLDS ASSAYS	
				oz./TON	oz./TON
0 - 3.0	Cont'd ser-sch - qtz strs, 50% qtz; py	4097	3.0	.22	)
3.0 - 8.0	Scr sch banded with 40% qtz, py, aspy	4098	5.0	.22	.21)
8.0 - 17.2	V.F.G. chl-ser sch, 10% qtz, py, sph, a little grey min.	4099	9.2	.07	.07)
17.2 - 26.0	Cont'd ser sch 60% qtz, alternating qtz with ser qtz, fair sulphides.	4100	8.8	.34	.32)
26.0 - 31.0	1 1/2 l/c chl-ser & ser sch - qtz bx, 40% qtz, dissem, py, aspy	4101	3.5/5.0	.23	.23)
31.0 - 34.0	chl-ser sch; sparse qtz and sulphides	4102	3.0	1.01	.96)
34.0 - 50.0	F.G. Sch gs almost mass 48 - 50				
50 - 57.0	Sch gs speckled text; alteratin				
57.0 - 60.0	Sl silic. gs-sch; dissem py & pyrrhotite				
60.0 - 68.0	" " " " py. 2 l/c				
68.0 - 70.0	Almost mass chl'e gs. 40% qtz; dissem py	4103	2.0	.03	
70.0 - 79.5	Chl - ser sch with increasing sch.				
79.5 - 81.0	Fine banded ser-qtz; 50% qtz, aspy	4104	1.5	.55	) .53)
81.0 - 87.0	buttons ditto 2 l/c	4105	4.0/6.0	.31	) .30)

LOGGED BY ASDHOLE No. U-B 192

FOOTAGE	DESCRIPTION	SAMPLE No.	SAMPLE LENGTH	GOLD ASSAYS	
				oz./TON	oz./TON
87.0 - 96.0	Narrow banded ser-qutz plus dark qutz bands. 60% qutz plus stal. py, aspy, grey min in dark qutz.	4106	9.0	.22	.21
96.0 -101.0	F. G. Ser sch, sparse qutz; some py; a few aspy xstls.	4107	5.0	.03	
101.0 -107.0	F.G. chl-ser sch; sparse qutz				
107.0 -111.0	Ser sch fine banding with 40% qutz, aspy, py	4108	4.0	.15	.15
111.0 -120.0	Ser'e & chl'e sch gs; dissempy, sparse qutz. 6 " 1.C				
120.0- 122.0	Ditto plus 3" band ser sch				
122.0 -130.0	Sl sch gs; b.s. alt. to 126				
		Calc. Aver.			
				Uncut	Cut
	<u>From</u>	<u>To</u>	<u>C.L.</u>		
	0	34.0	34.0	.29	.24
	79.5	96.0	16.5	.28	.26
	107.0	111.0	4.0	.15	.15