

2  
SHAFT \_\_\_\_\_  
250  
LEVEL \_\_\_\_\_  
B215N  
WORKING \_\_\_\_\_  
250N  
SECTION \_\_\_\_\_

DATE COMPLETED \_\_\_\_\_  
PURPOSE Low Angle Ore def.

FOOTAGE	DESCRIPTION	SAMPLE NUMBER	SAMPLE LENGTH	GOLD ASSAYS	
				OZ./TON	OZ./TON
0.0 - 24.0	grn chl sch				
24.0 - 73.0	gry-grn chl-ser sch				
73.0 - 108.0	gry-buff ser sch; T. S. 106.0 to 108.0	6405	2.0	.03	
108.0 - 114.0	90% qtz; sparing min; py, aspy., tr sp & gry min	6406	6.0	.34	2.040
114.0 - 118.0	as above	6407	4.0	.09	.360
118.0 - 125.0	as above	6408	7.0	.10	.700
125.0 - 132.0	as above	6408	5/7.0	1.04	7.280
132.0 - 137.0	as above	6409	5.0	.14	.700
137.0 - 140.0	30% qtz carb., minor min	6410	3.0	.04	<u>11.080</u>
140.0 - 141.0	grs sch w tan lent alt fl.				
	From      To      C.L.      Grade				
	108.0    137.0    29.0     .38				

Hole No. U-8585