

SHAFT 2

LAT. 13440.09

DATE COMPLETED _____

LEVEL 575

DIP AT COLLAR 45DEP. 7537.19

PURPOSE B-409Stope Dev.

WORKING B-409N

LENGTH 108.0

ELEV. 5446.5

SECTION 1575N

FOOTAGE	DESCRIPTION	SAMPLE NUMBER	SAMPLE LENGTH	GOLD ASSAYS																	
				OZ./TON	OZ./TON																
0-3.5	30% qtz; py, sp	7113	3.5	1.36																	
3.5-44.5	buff comp ser sch																				
44.5-51.5	20% qtz, py, a.py, sp	7114	7.0	.73																	
51.5-93.0	gry-buff ser sch; comp																				
93.0-98.0	30% qtz-carb; py, aspy	7115	5.0	.98	4.900																
98.0-102.5	as above w sp	7116	4.5	1.95	8.775																
102.5-106.0	60% dk qtz-carb; sp, gry min, v.g.	7117	3.5	.69	<u>2.415</u>																
					16.090																
106.0-108.0	gry ser sch merg w chl-ser																				
	<table><tr><td><u>From</u></td><td><u>To</u></td><td><u>C.L.</u></td><td><u>Grade</u></td></tr><tr><td>0</td><td>3.5</td><td>3.5</td><td>1.36</td></tr><tr><td>44.5</td><td>51.5</td><td>7.0</td><td>.73</td></tr><tr><td>93.0</td><td>106.0</td><td>13.0</td><td>1.23</td></tr></table>	<u>From</u>	<u>To</u>	<u>C.L.</u>	<u>Grade</u>	0	3.5	3.5	1.36	44.5	51.5	7.0	.73	93.0	106.0	13.0	1.23				
<u>From</u>	<u>To</u>	<u>C.L.</u>	<u>Grade</u>																		
0	3.5	3.5	1.36																		
44.5	51.5	7.0	.73																		
93.0	106.0	13.0	1.23																		

Hole No. U-81074