

TABLE 3. LABORATORY RESULTS OF SETTLED DUST ANALYSES

Surface Deposit Location	Arsenic Content of Settled Dust, % by weight	
	Soluble Fraction	Insoluble Fraction
Crushing Plant, Giant	0.006	1.39
Crushing Plant, Con - above screens	0.011	0.33
Cottrell, Giant	2.01	3.41
Baghouse, Giant - 1) near arsenic pump, on top of duct	62.6	1.60
2) near stairway to second level, on adjacent ledges	3.15	39.3