



ROYAL OAK MINES INC.

Yellowknife Division - Giant Mine

Mill Department

P.O. Bag Service 3000

Yellowknife, NWT

X1A 2M2

Fax #: (403) 920-2627

Telephone #: (403) 873-6301

Date: Feb. 09/93

Number of Pages (including cover sheet): 3

To: LARRY Connell

Fax #: \_\_\_\_\_

From: Connie - Have a nice Day! ☺

Comments:

IF ALL PAGES ARE NOT RECEIVED, PLEASE CALL (403) 873-6301-EXT 228

To: Larry Connell

Feb. 8, 1993

Calcine

Wash. Tickener O/F

			Tonnes/day
Jan	1	1993	179
	2		142
	3		415
	4		575
	5		512
	6		277
	7		461
	8		476
	9		200
	10		344
	11		236
	12		601
	13		477
	14		498
	15		441
	16		505
	17		462
	18		572
	19		430
	20		575
	21		372
	22		461
	23		578
	24		311
	25		672
	26		235
	27		338
	28		411
	29		437
	30		524
	31		399
Total			13,120
AVG			423 tpd

KK

To: Larry Connell

Feb. 8, 1993

## ① Settling test of Float Tails

Procedure: Time settling rate in a 1 l graduated cylinder without flocculant.

 $X = \frac{1}{2}$  cm      5 min = T

1 cm      10

2 cm      25


 $4\frac{1}{2}$  cm      32

5 cm      61

 $10\frac{1}{2}$  cm      127

13 cm      150

14 cm      181

 $14\frac{3}{4}$  cm      218② Size analysis of Float Tails  
80% wt - 200 Mesh③ Temp. of F.T       $15^{\circ}\text{C}$ 

④ Density of F.T      37% Solids

X X

