

Giant
YELLOWKNIFE MINES LIMITED

YELLOWKNIFE, N.W.T.
X1A 2M2

TELEPHONE 403-873-6301
TELEX:
PURCHASING 034-45503
OTHER DEPT. 034-45514

URGENT! ☐ AS SOON AS POSSIBLE ☐

08842

FROM W.L. Richardson ^{2/5}

DEPT. Assay

COPY TO K.G. Thomas;file

SEND TO

DATE

August 28-86

SUBJECT Gold on Baghouse Dust

MESSAGE

Weigh up a 5.0 gram sample of dust

~~Xxxx~~ Treat with 15mls of ~~Mx~~ HCl containing Stannous Chloride(90 grm./2 liters)

Boil on hot plate for 3-4 minutes: remove and cool slightly: add 10mls HNO₃(conc-)

return to hot plate for another 3-4 minutes: remove: rinse off watch glass and

filter contents into 125ml flask: dilute to 100mls with water: add 15mls M.I.B.K.

stopper flask with plastic stopper and shake for 5 minutes. Let layers separate and read via A.A.S.

As standard we use Calcine Residue(approx .15 oz./ton) treating in same manner.

Sample enclosed: MUST BE FIRE ASSAYED TO DETERMINE EXACT VALUE

REPLY

W. L. Richardson

4500E - 1

← SPEEDIMEMO →

MOORE SPEEDIPLY — 1 — MOORE CLEAN PRINT PATENTED 1963-1966

REPLY
FROM

DATE