

S.E. El-Alfy

April 13-88

To

Date

Copies To K. Morton; G. Deorksen; G. Halverson; file

Ref.

From W.L. Richardson

Subject Tailing Pond Drilling Account #46-01

Polishing Pond

x Au(oz./ton)			Au(oz./ton)		
Test Hole #4-1	0-20	.047	Test Hole #10-1	1-2	.033
2	1.8-4.8	.051	-2	4	.030
3	-7.8	.047	-3	6	.048
4	-10.8	.067	-4	8	.080
5	-13.8	.093	-5	10	.082
6	14-16	.077	-6	12	.075
7	18	.130	-7	14	.115
8	20	.105	-8	16	.090
9	21-24	.072	-9	18	.139
10	26	.119	-10	20	.119
11	28	.168	-11	22	.116
12	30	.082	-12	24	.118
13	32	.119	-13	26	.074
14	34	.122	x-14	28 clay	.022
15	36	.128			
x 16	36-? clay	.094	Test Hole #9-1	2-4	.047
x 17	38-40 clay	.048	-2	6	.053
			-3	8	.076
			-4	10	.063
Test Hole #5 grab 1-2		.022	-5	12	.101
±			-6	14	.112
5-1	2-4	.054	-7	16	.131
-2	6	.045	-8	18	.126
3	8	.061	-9	20	.099
-4	10	.059	-10	22	.099
-5	12	.109	-11	24	.125
-6	14	.126	-12	26	.079
-7	16	.095	-13	28	.117
-8	18	.154	-14	30	.088
-9	20	.146	-15	32	.094
-10	22	.101	-16	34	.089
-11	24	.080	-17	36	.117
-12	26	.099	-18	38	.132
-13	28	.107	-19	40	.099
-14	30	.088	-20	42	.104
x 15	29-31	.023	x-21	44 clay	.025

W.L. Richardson

x - not included